



Graver Technologies

Quality Department

**GRAVEX®
GR 1-1 US CI
CHLORIDE FORM**

SPEC NO	GTS-11-US-CI
REV NO	0
DATE	June 12, 2001
QA APPROVAL	<i>Keith Platoff</i>

PROPERTIES

Resin Type

Functionality

Matrix

Total Exchange Capacity

Water Retention

Particle Size

Whole Uncracked Beads

Metals (mg/dry kg)

Shipping Weight

SPECIFICATIONS

Strongly Basic Type I Anion Exchange Resin

Quaternary Ammonium

Styrene-Divinylbenzene

1.3 meq/mL (min)

50 - 60%

590 +/- 50 µm Mean Size

95% (min)

50 Sodium (max)

50 Iron (max)

10 Copper (max)

50 Aluminum (max)

42 lbs/ft³ (670 g/L)