



Graver Technologies

Quality Department

**POWDEX[®]
PAO
HYDROXIDE FORM**

SPEC NO	GTS-PX1000
REV NO	3
DATE	June 23, 2005

PROPERTIES

SPECIFICATIONS

Resin Type	Strongly Basic Anion Exchange Resin
Functionality	Quaternary Ammonium
Matrix	Styrene-Divinylbenzene
Total Moisture	50 – 60%
Total Exchange Capacity	4 meq/dry g (min)
Percent of Sites	95% Hydroxide (min)
	0.5% Chloride (max)
	0.5% Sulfate (max)
Metals (mg/dry kg)	50 Sodium (max)
	50 Iron (max)
	10 Copper (max)